

GLOBAL PAINT URETHANE ALKYD

EXTRA UV-PROTECTION | SCRATCH AND ABRASION RESISTANT |
PROVIDES GREAT HARDNESS AND ABRASION RESISTANCE

SUPERIOR HIDING POWER | EXCELLENT APPLICATION PROPERTIES |
QUICK DRYING PROPERTIES



| | |
|-----------------|----------------------------------------------------------------------------|
| Use | Indoor; Outdoor |
| Gloss | Semi-Gloss; High Gloss |
| Base | - |
| Color | All Colors |
| Sizes | ¼ Gallon; 1 Gallon |
| Suitable | Primed Wood; Metals; Multiplex; Window Frames; Doors; Kitchens; et cetera. |

PRODUCT INFORMATION

| | |
|-----------------------|-------------------------------------------------------------------------------------------------------|
| Binder | Modified urethane alkyd resin |
| Density | Approximately 1.2 kg per liter |
| Spreading rate | Approximately 10 – 12 m ² per liter depending on the porosity and surface of the substrate |
| Shelf life | 12 months in unopened packaging; Keep cool and dry during storage |

APPLICATION DETAILS

| | |
|--------------------------------------|----------------------------------------------------------------------------------------------------------------------------------------|
| Application methods | Brush; Roller; Spray; Spraying gun (pressure 2-3 bar, nozzle 1.5 mm-1.8 mm); Airless Spray (pressure 100 bar, nozzle 0.011-0.013 inch) |
| Drying properties | Dust dry after approximately 1 hour Tack Free after approximately 3 hours Recoat able after approximately 8 hours |
| Conditions during application | Not to be applied in the full sun Stir thoroughly before use |
| Thinner | White Spirit |
| Cleaning equipment | Clean brushes and equipment with mineral spirit |

SYSTEMS

Pre-treatment

- Surfaces to be primed must be clean, dry, and free of wax, grease, dust, mildew, and scaling paint
- Use **GLOBAL PAINT ALL CLEAN** as cleaning agent/degreaser. Glossy areas should be dulled
- Apply wood primer before and after filling nail holes, cracks, and other surface imperfections
- For best hiding results, tint the primer to the approximate shade of the finish coat, especially when a significant color change is desired
- Ensure all joints and seams are filled with a paint able caulking to prevent moisture ingress
- If excessive weathering has occurred exposing the original substrate the surface must be abraded and pre-treated with a suitable **GLOBAL PAINT UNIPRIMER**

Finish

- After this pretreatment the surface must be abraded and cleaned, for the best results apply at least two coats of **GLOBAL PAINT PU URETHANE ALKYD** or until a covered result is achieved